



# Physical Properties Surface Preparations

Physical Properties – Surface Preparations

SPECIFICATIONS							
PRODUCT	28 DAY BOND STRENGTH ASTM D-3931	28 DAY COMPRESSIVE STRENGTH ASTM C-109	ELONGATION	INITIAL SET AT 70°F (21°C)	FINAL SET AT 70°F (21°C)	POT LIFE AT 70°F (21°C)	APPROXIMATE COVERAGE RANGE AT 1/8" (3 MM)
CURELASTIC® 949	>140 psi (10 kg/cm²)	N/A	—	1 Hour	24 Hours	N/A	45-60 sq. ft. per gallon 4.1-5.5 m² per 3.78 L
FEATHEREDGE FASTSET 979	400 psi (28 kg/cm²)	4400 psi (324 kg/cm²)	—	15 Minutes	30 Minutes	10 Minutes	25-27 sq. ft. per 25 lb. bag 2.3-2.5 m² per 11.3 kg bag
LEVELCURE® LCB 951	400 psi (28 kg/cm²)	3700 psi (260 kg/cm²)	—	30 Minutes	2 Hours	10 Minutes	50-55 sq. ft. per 50 lb. bag 4.6-5.1 m² per 22.7 kg bag
LEVELCURE® SLU 961	500 psi (35 kg/cm²)	4650 psi (327 kg/cm²)	—	30 Minutes	2 Hours	10 Minutes	50-55 sq. ft. per 50 lb. bag 4.6-5.1 m² per 22.7 kg bag
PROFINISH 989	600 psi (42 kg/cm²)	3200 psi (225 kg/cm²)	—	15 Minutes	30 Minutes	15 Minutes	15 sq. ft. per 15 lb. pail 6.8 m² per 6.8 kg pail
PRO-RED® 963	N/A	N/A	>200%	1½ - 2 Hours	Water Testing 72 Hours	Indefinite	35-45 sq. ft. per gallon 3.2-3.7 m² per 3.78 L
SCRATCHCOAT 957	<b>7 DAY</b>		—	45 Minutes	24 Hours	45 Minutes	<b>AT 1/4" (6 MM)</b>
	215 psi (15 kg/cm²)	1908 psi (134 kg/cm²)					25 sq. ft. per 50 lb. bag 2.3 m² per 22.7 kg bag
ULTRACURE® 971	<b>ANSI A118.1</b>		>225%	Open to Light Traffic 24 Hours	Water Testing 72 Hours	6 Hours	<b>AT 30 MILS</b>
	400 psi (28 kg/cm²)	N/A					104 sq. ft. per 2 gallons 9.5 m² per 7.6 L
UNILAYMENT® 966	400 psi (28 kg/cm²)	3900 psi (274 kg/cm²)	—	30 Minutes	2 Hours	15 Minutes	50-55 sq. ft. per 50 lb. bag 4.6-5.1 m² per 22.7 kg bag
UNILAYMENT® FASTSET 969	400 psi (28 kg/cm²)	3900 psi (274 kg/cm²)	—	15 Minutes	30 Minutes	10 Minutes	25-27 sq. ft. per 25 lb. bag 2.3-2.5 m² per 11.3 kg bag

N/A = Not Applicable

### GUARANTEE

The recommendations, suggestions, statements and technical data are based on the best knowledge available to C-Cure and are given for informational purposes ONLY and without any responsibility for their use.

C-Cure MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT SOLD HEREIN except that the quality of the ingredients shall be in accordance with C-Cure specifications. It is expressly understood and agreed that the buyer's sole and exclusive remedy shall be replacement of defective products and under no circumstances shall

C-Cure be liable for incidental or consequential damages. C-Cure neither assumes nor authorizes any others to assume for it any liability with respect to furnishing of the product. Handling and use of the product are beyond the control of C-Cure, therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from the use of the product.

This writing constitutes a complete and exclusive statement of the understanding between C-Cure and buyer. There were no oral agreements or warranties, expressed or implied, collateral to or affecting the furnishing of the product. This understanding shall not be modified except in writing by an officer of C-Cure.

Members of National Tile Contractors Association, Materials & Methods Standards Association, Ceramic Tile Distributors Association.

NOTICE: The information in this bulletin is presented in good faith, but no warranty, express or implied, is given nor is freedom from any patent.

In as much as any assistance furnished by C-Cure with reference to the safe use and disposal of its products is provided without charge, C-Cure assumes no obligation or liability therefore, except to the extent that any such assistance shall be given in good faith.

**C-CURE**  
Seal Beach, CA 90740  
800-895-2874  
www.c-cure.com