



Physical Properties Additives

Physical Properties – Additives

| SPECIFICATIONS | | | | |
|-------------------------------|--|--|--|---|
| PRODUCT | SHEAR STRENGTH NON-VITREOUS TILES 28 DAY ANSI A118.4 | SHEAR STRENGTH VITREOUS TILES 28 DAY ANSI A118.4 | COMPRESSIVE STRENGTH PSI 28 DAY ASTM C-109 | APPROXIMATE MIXING RATIO (ESTIMATING) |
| PROGROUT ADDITIVE 945 | N/A | N/A | >3500 psi 246 kg/cm ² | 1.5 gallons per 50 lbs. 5.68 L per 22.7 kg |
| CURECRETE® 936 | >750 psi 53 kg/cm ² | >600 psi 42 kg/cm ² | >5000 psi 351.5 kg/cm ² | 1.5 gallons per 50 lbs. 5.68 L per 22.7 kg |
| CURECRYLIC® 938 | >400 psi 28 kg/cm ² | >700 psi 49 kg/cm ² | >4500 psi 316 kg/cm ² | .5 gallons per 25 lbs. 1.89 L per 11.3 kg |
| CURECRYLIC® PREMIUM 939 | >800 T/F | >350 psi 25 kg/cm ² | >3500 psi 246 kg/cm ² | 1.5 gallons per 50 lbs. 5.68 L per 22.7 kg |
| CURECRYLIC® ULTRA 940 | >750 psi 53 kg/cm ² | >600 psi 42 kg/cm ² | >4500 psi 316 kg/cm ² | 1.5 gallons per 50 lbs. 5.68 L per 22.7 kg |
| CUREFAST® 941 | >600 psi 42 kg/cm ² | >400 psi 28 kg/cm ² | >3500 psi 246 kg/cm ² | 1.5 gallons per 50 lbs. 5.68 L per 22.7 kg |
| PORCELAIN STONE & TILE 948 | >400 psi 28 kg/cm ² | >350 psi 25 kg/cm ² | >3500 psi 246 kg/cm ² | 2 gallons per 50 lbs. 7.6 L per 22.7 kg |
| CUREMIX® 937 | >750 psi 53 kg/cm ² | >650 psi 45 kg/cm ² | >3500 psi 246 kg/cm ² | 1.5 gallons per 50 lbs. 5.68 L per 22.7 kg |

N/A = Not Applicable
T/F = Tile Failure, Bond Intact

GUARANTEE

The recommendations, suggestions, statements and technical data are based on the best knowledge available to C-Cure and are given for informational purposes ONLY and without any responsibility for their use.

C-Cure MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT SOLD HEREIN except that the quality of the ingredients shall be in accordance with C-Cure specifications. It is expressly understood and agreed that the buyer's sole and exclusive remedy shall be replacement of defective products and under no circumstances shall C-Cure be liable for incidental or consequential damages. C-Cure neither assumes nor authorizes any others to assume for it any liability with respect to furnishing of the product. Handling and use of the product are beyond the control of C-Cure, therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from the use of the product.

This writing constitutes a complete and exclusive statement of the understanding between C-Cure and buyer. There were no oral agreements or warranties, expressed or implied, collateral to or affecting the furnishing of the product. This understanding shall not be modified except in writing by an officer of C-Cure.

Members of National Tile Contractors Association, Materials & Methods Standards Association, Ceramic Tile Distributors Association.

NOTICE: The information in this bulletin is presented in good faith, but no warranty, express or implied, is given nor is freedom from any patent. In as much as any assistance furnished by C-Cure with reference to the safe use and disposal of its products is provided without charge, C-Cure assumes no obligation or liability therefore, except to the extent that any such assistance shall be given in good faith.

C-CURE
Seal Beach, CA 90740
800-895-2874
www.c-cure.com