

Self-Leveling Underlayment 0 - 3/8" (0 - 9.5 mm)

PRODUCT DESCRIPTION

LEVELCURE® SLU Self-Leveling Underlayment is the state-of-the-art in Portland cement technology. With the sole addition of water, it becomes a free flowing liquid mortar that seeks its own level and produces a smooth flat surface. LEVELCURE SLU has been designed as an underlayment for the fast leveling and smoothing of floor surfaces with a minimum of labor required. The resulting finish is a smooth and durable surface that is acceptable for the installation of all floor coverings.

▶ BASIC USE

LEVELCURE SLU is used anywhere an uneven, rough or unfinished concrete surface must be leveled or smoothed before application of ceramic tile, marble, wood, resilient floor coverings or carpets. In addition to leveling concrete floors, LEVELCURE SLU can be used in rehabilitation projects where old terrazzo, ceramic tile, wooden floors and steel decking must be made ready for new floor coverings.

▶ AREAS OF USE

LEVELCURE SLU may be used on interior applications where a permanent water-resistant surface is required for receiving decorative floor coverings. LEVELCURE SLU hardens quickly by hydration (curing). Surfaces can be walked on in 2 to 4 hours and can have floor coverings installed within 12 to 24 hours. When cured, the finished underlayment will have similar properties to concrete. LEVELCURE SLU may be applied as thick as 3/8" (9.5 mm) to featheredge in a single application without fear of shrinking, cracking or spalling. Because its application requires no troweling, LEVELCURE SLU provides the installer considerable cost and time savings over conventional mortars and underlayments.

▶ LIMITATIONS

LEVELCURE SLU must not be used over gypsum based surfaces, old adhesive residue, paints, particle board, plastics, vinyl, epoxy or urethane floor coverings. Use in the temperature range of 40°F to 100°F (4°C to 38°C). (Do not allow mortar to freeze for the first 72 hours.) LEVELCURE SLU shall never be applied to any surface unless it has been previously primed with LEVELCURE PRIMER to provide adhesion to the substrate and allow the underlayment to retain water for improved flow and higher strengths. LEVELCURE SLU shall not be used as a wearing surface. LEVELCURE SLU is for interior use only. Do not use LEVELCURE SLU over substrates subject to hydrostatic pressure. The LEVELCURE SLU shall not be applied greater than 3/8" (9.5 mm) in a single pour.

▶ APPLICABLE STANDARDS

Color — Gray.

Texture — Powder, consisting of Portland cement, graded sand, organic and inorganic chemicals.

▶ PACKAGING

50 lb. (22.7 kg) multi-wall bags.

INSTALLATION

PREPARATORY WORK

All surfaces to receive LEVELCURE must be structurally sound. Deflection shall not exceed 1/360 of the span including live and dead load. Surfaces shall be free of dust, wax, sealers, old adhesive residue, curing compounds, oil, gypsum based underlayments, surface hardeners, paints, old flooring and other foreign material before application of primer.

▶ CONCRETE FLOORS

Concrete shall be completely exposed, fully cured (28 days minimum), free of moisture and efflorescence. Chip, sandblast or hammer out any spalled unsound concrete. Clean off any resulting dust. Smooth, steel troweled concrete floors must be roughened to ensure a good bond. Prime cleaned surface with LEVELCURE PRIMER diluted 1 to 1 with water. Apply even coat using brush or broom. On extremely porous concrete, two applications may be required. Allow LEVELCURE PRIMER to dry to tacky surface before applying LEVELCURE SLU. Reapply LEVELCURE PRIMER if first application is allowed to dry past 24 hours.

▶ MASONRY SURFACES

Dilute LEVELCURE PRIMER 1 to 1 by volume with water. Apply even coat to clean surface using brush or broom. Allow to dry to tacky surface before applying LEVELCURE SLU.

▶ PLYWOOD

Plywood surfaces shall be of exterior grade, and when placed over conventional floor joists, shall be of a design and thickness to provide a secure, rigid substrate base. Allow a gap of 3/16" to 1/4" (5 to 6 mm) between sheets of plywood. Fill these gaps with C-Cure QUICKCURE 908 dry-set mortar. Prime the plywood subfloor with LEVELCURE PRIMER 943 diluted at the ratio of 1:1 with water.

After the primer has dried, nail or staple thin, galvanized metal lath or C-Cure ProLATH 950 to the floor. Next, mix 1 qt (0.95 L) of LEVELCURE PRIMER with 5 1/2 qts. (5.2 L) of water to 1 bag of LEVELCURE SLU powder; mix as normal. Install no less than 1/4" (6 mm) nor more than 1" (25 mm) thickness of the above LEVELCURE SLU mix over the surface following the standard procedure.

▶ SPECIAL SURFACES

Marble, terrazzo and existing ceramic tile surfaces must be well bonded to the subfloor, cleaned of any waxes and abraded to a rough surface prior to priming. Prime the surface. First, dilute LEVELCURE SLU at the ratio of 1 gal. (3.8 L) primer to 1/2 gal. (1.89 L) water, then mix in 1 1/2 gal. (5.68 L) of LEVELCURE powder. (*Metal lath is not necessary.*) Broom this primer slurry over the subfloor. Let dry, then apply LEVELCURE SLU as for concrete floors. Over steel surfaces, consult with C-Cure's Technical Service Department to discuss the particular job conditions. DO NOT USE over particle board, plastic, vinyl, urethane or epoxy floor coverings.

▶ MIXING

Mix one 50 lb. (22.7 kg) bag of LEVELCURE SLU with a measured amount of water primer/water blend not to exceed 6 qts. (5.68 L) (*A slight reduction in amount of water used may be necessary due to cooler weather conditions.*) Always add the powder to the total amount of liquid and mix with a 650 RPM power mixer until a lump-free mix is obtained. Experience shows that it is best to mix only 2 bags of LEVELCURE SLU at a time, pour this on the floor, then mix as many additional 2 bag batches as necessary to complete the job. For optimum mixing results, it is advisable to use a C-Cure mixing paddle for the minimal air entrapment in the mortar. For information on pumping LEVELCURE SLU, consult C-Cure's Technical Department.

▶ APPLICATION

Pour the underlayment approximately in place and then finish with C-Cure's adjustable mortar spreader. Spiked shoes should be used if it is necessary to walk in the fresh mortar. A finish blade may be used for featheredging. LEVELCURE SLU will have a flow time of approximately 10 minutes. The finished floor will be ready to walk on in 2 to 4 hours and floor covering may be installed 12 to 24 hours later. Ceramic tile installed with C-Cure dry-set mortar system may be installed on LEVELCURE SLU when mortar is firm enough to walk on. For thicker applications over 3/8" (9.5 mm) up to 1" (25 mm) thick, use LEVELCURE LCB. LEVELCURE SLU shall only be applied over substrates that are between 40°F to 100°F (4°C to 38°C). Do not allow LEVELCURE SLU to freeze for the first 72 hours. If application of LEVELCURE SLU is to exceed 3/8" (9.5 mm) in nominal areas, multiple application layers not greater than 3/8" (9.5 mm) per pour shall be used. Each pour shall cure a minimum of 24 hours and the surface of each previous layer must be primed with LEVELCURE PRIMER prior to application of subsequent pours. When multiple application pours {2 or more} are to be used to achieve

an entire floor thickness 3/8" to 1" (9.5 to 25 mm), it is suggested that a single pour of LEVELCURE LCB be used.

► **APPLICATION IN LARGE AREAS**

After primer has been applied, create dams (using wood or weather stripping tape) across the width of the room spacing the dams 10 ft. (3 m) apart. Apply LEVELCURE SLU in the odd numbered swaths created by the dams and allow material to cure beyond its flow time. Then remove the dams and apply LEVELCURE SLU to the even numbered swaths using a "striker" to blend the material at the seams.

► **EXPANSION JOINTS**

Expansion joints, saw cut, cold joints or structural cracks shall never be bridged over with LEVELCURE SLU. They should continue through the LEVELCURE SLU and subsequent tile work. All joints through the self-leveling underlayment and tile work directly over structural joints must never be narrower than the structural joint. Provide expansion joints 20 to 24 ft. (6 to 7.3 m) in each direction. Where floor is exposed to direct sunlight or moisture, provide expansion joints 12 to 16 ft. (3.6 to 4.9 m) in each direction. Install expansion joints where LEVELCURE SLU abuts restraining surfaces such as perimeter walls, dissimilar floors, curbs, columns and pipes. An architect or structural engineer must specify expansion joints and show location and details on drawings.

► **CLEANING**

Water is all that is needed to remove uncured LevelCure.

► **CURING**

A minimum cure is obtained in 12 to 24 hours, depending on ambient temperatures. As with concrete, the strength increases significantly with age during the first 28 days. Always check for moisture prior to installation of vinyl flooring.

NOTE: Do not add any other materials to LEVELCURE LCB other than those prescribed by C-Cure. For conditions other than those covered in the instructions, refer to C-Cure's Technical Service Department.

► **COVERAGE**

LEVELCURE SLU will cover approximately 50 to 55 sq. ft. (4.6 to 5.1 m²) per 50 lb. (22.7 kg) bag at 1/8" (3 mm) thickness. LEVELCURE Primer will cover approximately 250 - 300 sq. ft. (23 to 28 m²) per gal. (3.8 L) over smooth concrete.

► **WARRANTY**

LEVELCURE SLU 961 is included in C-Cure's Five Year System Warranty. For terms and conditions see Warranty Document #WRTDS.

LevelCure® SLU 961

Self-Leveling Underlayment 0 - 3/8" (0 - 9.5 mm)

LEVELCURE SLU 961 TECHNICAL DATA			
TEST		TYPICAL VALUES	
A.	Working Time @ 70°F (21°C)	20 Minutes	
B.	Flowing Time @ 70°F (21°C)	10 Minutes	
C.	Initial Set @ 70°F (21°C)	30 Minutes	
D.	Final Set @ 70°F (21°C)	2 Hours	
E.	Compressive Strength ASTM C109	3 Days 7 Days 28 Days	2075 psi (146 kg/cm ²) 3225 psi (227 kg/cm ²) 4650 psi (327 kg/cm ²)
F.	Flexural Strength ASTM C-348	28 Days	1035 psi (73 kg/cm ²)
G.	Tensile Strength ASTM C190	28 Days	520 psi (37 kg/cm ²)
H.	Bond Strength ASTM D3931	28 Days	500 psi (36 kg/cm ²)
I. Safety—CAUTION: May cause eye, skin or lung injury. Contains free silica. Prolonged exposure to dust may cause delayed lung disease (silicosis). Eliminate exposure to dust. Use NIOSH approved mask for silica dust. Contains Portland cement. If any cement or cement mixtures get into eye, flush immediately and repeatedly with water, and consult a physician promptly. Freshly mixed cement, mortar, concrete or grout may cause skin injury. Avoid contact with skin where possible and wash exposed skin areas promptly with water.			
KEEP OUT OF REACH OF CHILDREN.			
J. Storage Life—One year if kept dry in sealed bags.			

GUARANTEE

The recommendations, suggestions, statements and technical data are based on the best knowledge available to C-Cure and are given for informational purposes ONLY and without any responsibility for their use.

C-Cure MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT SOLD HEREIN except that the quality of the ingredients shall be in accordance with C-Cure specifications. It is expressly understood and agreed that the buyer's sole and exclusive remedy shall be replacement of defective products and under no circumstances shall C-Cure be liable for incidental or consequential damages. C-Cure neither assumes nor authorizes any others to assume for it any liability with respect to furnishing of the product. Handling and use of the product are beyond the control of C-Cure, therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from the use of the product.

This writing constitutes a complete and exclusive statement of the understanding between C-Cure and buyer. There were no oral agreements or warranties, expressed or implied, collateral to or affecting the furnishing of the product. This understanding shall not be modified except in writing by an officer of C-Cure.

Members of National Tile Contractors Association,

Materials & Methods Standards Association, Ceramic Tile Distributors Association.

NOTICE: The information in this bulletin is presented in good faith, but no warranty, express or implied, is given nor is freedom from any patent. In as much as any assistance furnished by C-Cure with reference to the safe use and disposal of its products is provided without charge, C-Cure assumes no obligation or liability therefore, except to the extent that any such assistance shall be given in good faith.

C-CURE
Seal Beach, CA 90740
800-895-2874
www.c-cure.com